

APPENDIX B
Substitute Specification
(Red-Lined Version)

Attorney Docket No. 9281-4210
Liquid Crystal Display Apparatus Having
Flexible Substrate
Inventor Tetsushi Tanada et al.

09975344-101001

LIQUID CRYSTAL DISPLAY APPARATUS HAVING FLEXIBLE SUBSTRATE

BACKGROUND OF THE INVENTION

1. FIELD OF THE INVENTION

This invention relates to a liquid crystal display apparatus having a flexible substrate.

2. DESCRIPTION OF THE RELATED ART

A liquid crystal display apparatus that consumes minimal power has been used currently as a display unit for a portable electronic apparatuses such as portable information terminals or cellular phones as a display unit. ~~Particular in the case of a~~ In particular, reflection type liquid crystal apparatuses that does not need are used for most products as a backlight and can be operated with more is not necessary, resulting in minimal power consumption, ~~the liquid crystal display apparatus is used for almost all products because and increased battery life duration time of an electronic apparatus can last longer.~~

Meanwhile, ~~with recent increasing request for miniaturization and light weight of the electronic apparatus, the~~ a liquid crystal display apparatus that employs a resin film substrate instead of a conventional glass substrate has been developed to answer the ever-increasing need for further miniaturization and weight decrease of the electronic apparatus.

~~An exemplary configuration~~ One example of a reflection type liquid crystal display apparatus having a film substrate

as described hereinabove will be described briefly with reference to FIG. 3. FIG. 3 is a diagram showing ~~the a~~ partially cross-sectional ~~configuration view~~ of a liquid crystal display apparatus having a conventional configuration. In FIG. 3, the liquid crystal display apparatus 100 comprises a first film substrate 110 and a second film substrate 120, which ~~are faced~~ each other, and a liquid crystal layer 130 that is sealed between the two film substrates 110 and 120.

~~On the side of the first film substrate 110 of the liquid crystal layer 130, an A laminated structure of an electrode layer 115 consisting of transparent conductive films such as ITO (indium-tin oxide) that is served to operates liquid crystal molecules of the liquid crystal layer 130 and an orientation film 116 that is served to controls the orientation of liquid crystal molecules of the liquid crystal layer 130 are formed successively to form the laminated structure are formed on the liquid crystal layer side of the first film substrate 110. Furthermore, Another laminated structure of an electrode layer 125 and orientation film 126 are formed on the liquid crystal layer 130 side of the second film substrate 120, an electrode layer 125 and orientation film 126 are formed successively to form the laminated structure. Furthermore, a reflection plate 128 is provided on the opposite side of the second film substrate 120 (the outer face side of the second film substrate 120) to the liquid crystal layer 130 with respect to the second~~

~~film substrate 120, a deflection plate 128 is provided.~~

Furthermore, a reflector 140 having one surface on which a reflection film 141 of aluminum is formed on the outer face side of the first film substrate 110.~~a reflector 140 having one surface on which a reflection film 141 consisting of aluminum is formed is provided so that the~~An adhesive 142 is formed between the reflection film 141 is facing to and the substrate 110 with interposition of adhesive 142.

The liquid crystal display apparatus 100 having the above-mentioned configuration has been used as ~~the a~~ a reflection type liquid crystal display apparatus, in which ~~solar light energy or other external illumination is used as the light source. and the light that is~~ Light incident from the outside of the second substrate 120 is reflected on the reflection film 141 and used for displaying.

Furthermore, because ~~of a film substrate that is thinner than a conventional glass substrate is used as the substrate of a liquid crystal apparatus and a substrate that is thinner than a glass substrate can be used,~~ it is possible to make an electronic apparatus having the above-mentioned liquid crystal display apparatus thin, and parallax is suppressed to bring about ~~the a~~ a high quality display.

However, according to the configuration of the liquid crystal display apparatus 100, because the exterior type reflector 140 reflects the incident light, the light incident from the second substrate 120 side to the liquid crystal

display apparatus 100 passes through the two substrates 110 and 120 and a reflection plate 128 inevitably before the light reaches ~~to the~~ reflection film 141 of the reflector 140. As the result, the light transmission loss is large, and the brightness of the display is insufficient.

Furthermore, because the liquid crystal display apparatus 100 comprising the above-mentioned film substrate is a component used as the display unit of, for example, a cellular phone and ~~the~~ low cost is required, it is very important to simplify the configuration and manufacturing process of the liquid crystal display apparatus so that the cost is reduced.

The present invention has been accomplished to solve the above-mentioned problems, and it is an object of the present invention to provide a liquid crystal display apparatus having a flexible substrate that is capable of displaying ~~the~~ high quality images with high brightness.

It is another object of the present invention to provide a liquid crystal display apparatus having ~~the a~~ simplified configuration that ~~brings about the~~ reduces manufacturing costs reduction.

SUMMARY OF THE INVENTION

To achieve the above-mentioned object, a liquid crystal display apparatus according to a first aspect of the present invention ~~is characterized in that the liquid crystal display apparatus comprises a pair of substrates disposed so as to face each other with interposition of a~~

liquid crystal layer, at least one of the substrates is a flexible substrate, ~~wherein many~~ and a plurality of concave faces each having the a spherical inner surface that is a part of the spherical surface are and formed continuously on the surface of at least one substrate ~~out of the pair of substrates that is facing to the liquid crystal layer side.~~

According to the configuration in accordance with the present invention, because ~~many~~ the concave faces having the inner surface that is a part of the spherical surface are formed continuously on one surface of a flexible substrate, the configuration of the liquid crystal display is simplified to bring about the reduced manufacturing cost.

Next, the liquid crystal display apparatus according to a second aspect ~~is characterized in that the liquid crystal display apparatus according to the first aspect has a metal reflection film formed on the substrate surface on which many concaves having the inner surface that is a part of the spherical surface are formed continuously.~~

According to the above-mentioned configuration, the reflection type liquid crystal display apparatus of the present invention ~~is served as a reflection type liquid crystal display apparatus having~~ has a built-in reflection plate for reflecting the light between the pair of substrates. Because the metal reflection film is shaped as described hereinabove, the reflection efficiency of the metal reflection film is improved to bring about ~~the a~~ a bright

display.

Next, the liquid crystal display apparatus according to a third aspect ~~is characterized in that the liquid crystal display apparatus according to the second aspect~~ has a depth of the concave faces ranging from $0.1\mu\text{m}$ to $3\mu\text{m}$, an inclination distribution of the inner surface of the concave faces ranging from -30 degrees to +30 degrees, and a pitch between adjacent concave faces ranging from $5\mu\text{m}$ to $50\mu\text{m}$.

According to the configuration as described hereinabove, because the reflection efficiency of the metal reflection film is optimized, the light incident from the outside is reflected efficiently, and ~~the a~~ bright reflection display is realized.

Next, the liquid crystal display apparatus according to a fourth aspect ~~is characterized in that the liquid crystal display apparatus according to the second aspect~~ has the a metal reflection film having a film thickness ranging from 80 \AA to 300 \AA .

According to the configuration as described hereinabove, because the film thickness of the metal reflection film is made very thin, ~~the a~~ bright transmission display is realized and the metal reflection film ~~is possible to reflect~~ the light efficiently even ~~in the case that when~~ a light source ~~that is served for transmission display is disposed outside~~ used that is external to the substrate to fabricate a semi-transmission/reflection type liquid crystal display apparatus. In other words, a

semi-transmission/reflection type liquid crystal display apparatus that gives ~~the~~ a bright and easily visible display for both transmission display and reflection display is realized.

Next, the liquid crystal display apparatus according to a fifth aspect ~~is characterized in that the liquid crystal display apparatus according to the second aspect~~ has a metal reflection film with a film thickness ranging from 80 Å to 100 Å.

According to the configuration as described hereinabove, a semi-transmission/reflection type liquid crystal display apparatus that gives ~~the~~ a bright reflection display and an extraordinarily bright transmission display is realized.

Next, the liquid crystal display apparatus according to a sixth aspect ~~is characterized in that the liquid crystal display apparatus according to any one of second aspect to fifth aspect~~ has a color filter formed directly on the metal reflection film.

According to the configuration as described hereinabove, because the color filter is formed on the surface on which ~~the~~ light incident from the outside is reflected, the parallax and color deviation is minimized and the high quality display is realized.

Next, the liquid crystal display apparatus according to a seventh aspect ~~is characterized in that the liquid crystal display apparatus according to any one of first~~

aspect to sixth aspect has a colored substrate having with the surface on which ~~many the concave faces having the inner surface that is a part of the spherical surface~~ are formed continuously.

According to the configuration as described hereinabove, the color of the colored substrate may be used as the display color in the case that a reflection type liquid crystal display apparatus is fabricated. In other words, ~~the a~~ display having the color purity higher than that of the display obtained by means of orientation control of liquid crystal molecule is realized.

Next, the liquid crystal display apparatus according to a eighth aspect ~~is characterized in that the liquid crystal display apparatus according to the first aspect has the a~~ flexible substrate ~~consisting of~~ comprising polyallylate base, polycarbonate base, polyethersulphone base, or polyethylene terephthalate base resin.

According to the configuration described hereinabove, because the resins described hereinabove are highly transparent, the bright display is realized for both reflection display and transmission display. Furthermore, because the above-mentioned resin materials are excellent in heat resistance and a film can be formed at a high temperature, a high quality liquid crystal display apparatus is realized.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a diagram showing a partial cross sectional

configuration of a liquid crystal display apparatus in accordance with an embodiment of the present invention.

FIG. 2 is a partially enlarged perspective view showing a substrate including the convex/concave faces shown in FIG. 1.

FIG. 3 is a diagram showing the partially cross sectional configuration of an exemplary reflection type liquid crystal display apparatus having a conventional flexible substrate.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

One embodiment of the present invention will be described in detail hereinafter with reference to FIG. 1. However, the present invention is by no means limited to the embodiment described hereinafter. The drawings that will be referred in the present specification are presented only for describing the liquid crystal display apparatus. Structural components, the magnitude of dimension, size, and thickness of elements shown in the drawings ~~are~~ may be different from those of the actual liquid crystal display apparatus.

FIG. 1 is a diagram showing a ~~partially~~ cross sectional ~~configuration view~~ of a liquid crystal display apparatus in accordance with an embodiment of the present invention. In FIG. 1, a liquid crystal display apparatus 1 comprises a liquid crystal layer 30 interposed between a first substrate 10 and second substrate 20 ~~that are faced each~~ other, and the peripheries of the two substrates 10 and 20

are bonded together with sealing material 40. The two substrates 10 and 20 consist of flexible resin in the present embodiment, but a glass substrate may be used as the second substrate 20.

A convex/concave face 10A is formed on the liquid crystal layer 30 side of the above-mentioned first substrate 10, and the convex/concave face 10A is shaped so that the many plurality of concave faces, each of which constitutes a part of a spherical surface, are formed continuously. A laminated structure containing ~~On the convex/concave face 10A,~~ a metal reflection film 12 for reflecting the incident light that comes from the outside, a color filter 13 for displaying colors, an overcoat film 14 for protecting and flattening the film surface of these films, an electrode layer 15 for driving the liquid crystal layer 30, and an orientation film 16 for controlling the orientation of liquid crystal molecules that constitute the liquid crystal layer 30 ~~are is formed in laminated fashion on the convex/concave face 10A.~~ Another laminated structure containing ~~On the liquid crystal layer 30 side of the second substrate 20,~~ an electrode layer 25, an overcoat film 24, and an orientation film 26 ~~are is formed successively to form the laminated structure on the liquid crystal layer 30 side of the second substrate 20.~~ Furthermore, on the outer face side (upper side in the drawing) of the second substrate 20, a phase difference plate 27 ~~served for controlling that controls~~ the wavelength dispersion of the light, and a deflection

reflection plate 28 ~~served for controlling~~ that controls
~~deflection-reflection~~ of the light are laminated in the
order.

The first substrate 10 preferably consists of a
material that is highly transmissive to the light (preferably
90 % or higher, same as that of a glass) and is heat resistive
at a temperature of 200 °C or higher. If a less transmissive
material ~~that is less transmissive~~ is used, the light loss
of the light incident from the outside ~~due to traveling of~~
~~the light that travels~~ through the liquid crystal display
apparatus 1 is large and the display is dark. If a material
that is not resistive to a temperature of 200 ° C or higher,
the resistivity of the transparent conductive film used as
the electrode layer 15 ~~becomes large~~ increases and the power
consumption is large.

Particularly, a transparent conductive film such as
ITO is used as the electrode layer 15, ~~and~~. Note that an
ITO film formed at a low film-forming temperature exhibits
significantly larger resistivity in comparison with ITO
formed at a high temperature of 200 ° C or higher.
Furthermore, if the film thickness is increased to reduce
the resistivity of ITO formed at a low temperature, the
increased film thickness causes ~~the reduced light~~
transmittance and warpage of the substrate 10 due to stress
of the electrode layer 15. As described hereinabove, the
heat resistance of the substrate 10 is very important, and
the quality of the liquid crystal display apparatus 1 depends

significantly on the heat resistance of the substrate 10.

Examples of the material preferably used for the above-mentioned first substrate 10 include resin materials such as polyallylate base resin, polyether-sulphone base resin, polyethylene-terephthalate based resin, and polycarbonate base resin, but the material is by no means limited to those resins. Polyallylate base resin is used more preferably because the heat resistance temperature is as high as 280 ° C, the light transmittance is as high as 90 % or higher, and the birefringence is as low as 0.

The first substrate 10 is formed of the above-mentioned material, and ~~the~~ a gas barrier layer consisting of silicone oxide film or silicon nitride film may be formed on one side or both sides of the first substrate 10. The configuration having the above-mentioned gas barrier layers on the substrate 10 excludes ~~the~~ adverse effects on the liquid crystal layer 30 due to de-gassing from the above-mentioned resin material or gas that penetrates into the liquid crystal display apparatus 1 through the above-mentioned resin material from the outside. As the result, the reliability of the liquid crystal display apparatus 1 is improved.

Although a different material, such as glass, may be used as the second substrate 20, preferably ~~The same material used for the above-mentioned first substrate 10 may be used also for the~~ and second substrate 20 are formed of the same material preferably, but different material such

09975344-104004

~~as glass may be used depending on the case. In the case~~
~~that~~If the same material is used for the first substrate
~~10 is used also for~~and the second substrate 20, a liquid
~~crystal display apparatus that is excellent in the~~
~~reliability can be obtained because the thermal expansion~~
~~coefficient of the two substrates 10 and 20 is identical.~~
~~to~~This results in less rupture of the circuit due to the
caused by changes in the ambient environment temperature
change.

Furthermore, the first substrate 10 disposed on the
back face side of the liquid crystal display apparatus 1
may be pigmented. For example, if the substrate 10 is
pigmented black to obtain the a black display, having the
color purity is higher than that of the a black display
expressed by means of dcreated by reflection control by use
of the liquid crystal molecules, and thereby realizing a
liquid crystal display apparatus with an excellent in display
quality with and improved contrast is realized.

The electrode layer 15 comprises a plurality of
aligned many-flat rectangular transparent conductive films
consisting of ITO, and is which may be connected individually
to an external driving circuit (not shown in the drawing).
Furthermore, the electrode layer 25 formed on the second
substrate 20 also comprises a plurality of aligned many-flat
rectangular transparent conductive films like the
above-mentioned electrode layer 15, and is connected
individually to an external driving circuit. The electrode

layer 15 and the electrode layer 25 are disposed ~~so as to~~ make a right angle with each other (in ~~the a~~ plan view), and ~~the a~~ passive matrix type liquid crystal display apparatus 1 is formed ~~in the passive matrix type~~.

In the liquid crystal display apparatus in accordance with the present invention, because the substrate 10 and/or the substrate 20 is formed of resin material with high heat resistance as described hereinabove, it is possible to form the transparent conductive film at a high temperature. As the result, the electrode layers 15 and 25 having the light transmittance and resistivity equivalent to those of the transparent conductive film formed on a glass substrate at a high temperature can be obtained and ~~the a~~ high performance liquid crystal display apparatus is realized.

The overcoat film 14 of the first substrate 10 and the overcoat film 24 of the second substrate 20 are provided to equalize the thickness of the liquid crystal layer 30 by flattening the irregular thickness of the substrates 10 and 20 and layers formed on those substrates 10 and 20.

~~In the case that~~ If the substrates 10 and 20 of the liquid crystal display apparatus 1 are formed of resin material, because ~~it is required to avoid the adverse effects~~ due to caused by degassing from the above-mentioned resin material on the liquid crystal layer 30, the above-mentioned overcoat films 14 and 24 are formed ~~so as to~~ cover the ~~one~~ entire liquid crystal layer side surface of each of the substrates 10 and 20 ~~directed to the liquid crystal layer~~

09975344-101001

~~30-side~~. The overcoat films 14 and 24 formed ~~so as to cover~~
~~the onethis surface of each of the substrates 10 and 20~~ prevent
degassing from the substrates 10 and 20 and penetration to
the liquid crystal layer 30, and ~~the~~ deterioration due to
degassing of the liquid crystal layer 30 is prevented.

The metal reflection film 12 is provided to
efficiently reflect ~~the~~ light incident from the outside onto
the liquid crystal display apparatus 1 to obtain ~~the a~~ bright
display, and is formed on the convex/concave face 10A that
is formed on the liquid crystal layer ~~30-side~~ of the first
substrate 10 as shown in FIG. 1. The metal reflection film
12 may consist preferably of a metal material with high
reflection such as aluminum or silver. Furthermore, the
metal reflection film 12 is formed by ~~spattering~~ sputtering
or vacuum evaporation of these metals.

Furthermore, the metal reflection film 12 is
preferably formed only on the convex/concave face 10A that
is the one convex/concave-shaped face of the substrate 10
as shown in FIG. 1. The reason is that the outer end of
the metal reflection film 12 formed on the entire surface
of the liquid crystal layer 30 of the substrate 10 is exposed
directly to the outside air and the metal reflection film
12 can be oxidized from the outer end to result in separation
of the film 12.

Furthermore, the color filter 13 is formed directly
on the metal reflection film 12. The color filter 13 can
be disposed on the reflection surface (the surface of the

metal reflection film 12) that reflects the light incident from the outside because of the above-mentioned structure, and the color deviation and parallax can be reduced. As the result, the liquid crystal display apparatus 1 of the present invention displays ~~the~~ high quality images.

The thickness of the metal reflection film 12 ranges preferably from 80Å to 300 Å.

The above-mentioned film thickness allows the display to be viewed easily and brightly for both reflection displaying and transmission displaying in the case that a semi-transmission/reflection type display apparatus provided with a backlight on the outside of the substrate 10 is fabricated. The metal reflection film 12 can be formed very thin as described hereinabove because of the configuration of the convex/concave face 10A of the first substrate 10. In other words, the thinner film thickness of the metal reflection film 12 results in reduced reflectance of the metal reflection film 12, but the above-mentioned convex/convex shape of the metal reflection film 12 brings about higher light reflectance. As the result, it is possible to display an image with ~~the~~ a brightness higher than that of ~~the~~ a conventional apparatus even if the film thickness of the metal reflection film 12 is formed thin.

Furthermore, the very thin film thickness (as thin as 80 Å to 100 Å) of the metal reflection film 12 renders the metal reflection film 12 highly transmissive, and ~~the~~

09975344 " 101001
FOOTOT " 44352600
a very bright display is realized for ~~the~~ transmission displaying.

As described hereinabove, the liquid crystal display apparatus of the present invention realizes the bright and easy-viewing display also in the case that a semi-transmission/reflection type liquid crystal display apparatus provided with a backlight on the outside of the substrate 10 is fabricated.

The film thickness range of the metal reflection film 12 described hereinabove is suitable for the semi-transmission/reflection type liquid crystal display apparatus that is used for both reflection display and transmission display, ~~but in~~ In the case of ~~the a~~ reflection type liquid crystal display apparatus ~~that is used only for~~ reflection display, the film thickness is not limited and, for example, a film thickness of 1000 Å ~~film thickness may be applied~~ used.

The reflection type liquid crystal display apparatus provided with ~~the a~~ metal reflection film 12 is described in the present embodiment, but the metal reflection film 12 may be omitted. If the metal reflection film 12 is omitted, the liquid crystal display apparatus 1 is used as a transmission type liquid crystal display apparatus. In such case, the light is scattered effectively by means of the above-mentioned convex/concave face 10A and a transmission type liquid crystal display apparatus excellent in white display is realized.

Furthermore, the inner surface of ~~many~~ each of the concave faces of the above-mentioned convex/concave face 10A is spherical. This is to say that each inner surface is a part of ~~the~~ a spherical surface, and thus the surface functions as a lens to intensify ~~the~~ light incident from the outer face side of the first substrate 10, and making ~~it is~~ possible to render the display bright. As described hereinabove, because the convex/concave face 10A functions to intensify the light, the liquid crystal display apparatus of the present invention can realize the bright display with a reduced backlight intensity that is provided on the outside of the substrate 10 for transmission display. As the result, it is possible to reduce the power consumption of the backlight, which consumes the power for the liquid crystal display apparatus mostly, and ~~the~~ a low power consumption liquid crystal display apparatus is realized.

The configuration of the convex/concave face 10A shown in FIG. 1 will be described in detail with reference to FIG. 2. FIG. 2 is a perspective view showing the first substrate 10 and the part including the metal reflection film 12 formed on the first substrate 10. As shown in FIG. 2, the inner face of ~~many~~ the concave faces 12A, each of which is a part of the spherical surface, is formed continuously on the surface of the convex/concave ~~faces~~ face 10A of the substrate 10 ~~so as~~ to overlap each other, and the metal reflection film 12 is laminated on the surface.

It is preferable that the depth of the above-mentioned

concave faces 12A is formed randomly in the range from 0.1 μm to 3 μm , the pitch between adjacent concave faces 12A is disposed randomly in the range from 5 μm to 50 μm , and the inclination of the inner surface of the above-mentioned concave faces 12A is set in the range from -30 degrees to 30 degrees.

Particularly setting of the inclination distribution of the inner face of the concave faces 12A in the range from -30 degrees to 30 degrees and the random disposition of the pitch of the adjacent concave faces 12A in all directions in a plane are important. The reason is that, if the pitch of the adjacent concave faces 12A is regular, the reflected light is colored due to interference color of the light. Furthermore, if the inclination distribution of the inner face of the concave faces 12A deviates from the range from -30 degrees to 30 degrees, the diffusion angle of the reflected light is too wide and results in reduced reflection intensity and bright display cannot be obtained (the diffusion angle of the reflected light is equal to or larger than 60 degrees to result in reduced reflection intensity peak in the liquid crystal display apparatus and result in large total reflection loss).

Furthermore, if the depth of the concave faces 12A exceeds 3 μm , the peaks ~~of the convex~~ cannot be buried with the flattening film (overcoat film 14) when the concave faces 12A ~~is~~ are flattened in the subsequent process step, ~~and~~. As a result, the desired flatness cannot be obtained and

the ~~a~~ depth that exceeds $3\text{ }\mu\text{m}$ causes the display to be irregular display.

If the pitch of the adjacent concave faces 12A is less than $5\text{ }\mu\text{m}$, the fabrication work for making a transfer die that is used for forming the convex/concave ~~faces 10A~~ face 10A of the first substrate 10 is limited, and the working time ~~should be long~~ increases. Furthermore, the shape for obtaining desired reflection characteristic cannot be formed and ~~the~~ interferential light is caused. Furthermore In addition, ~~in the case that as a diamond indenter~~ having a diameter of $30\text{ }\mu\text{m}$ to $100\text{ }\mu\text{m}$ ~~that is usable~~ used to fabricate the transfer die ~~is used~~, it is preferable that the pitch is in the range from $5\text{ }\mu\text{m}$ to $50\text{ }\mu\text{m}$ between the adjacent concave faces 12A.

In the case of the liquid crystal display apparatus 1 of the present invention, because the metal reflection film 12 formed on the convex/concave ~~faces 10A~~ face 10A of the first substrate 10 is shaped in a convex/concave fashion ~~by means of the convex/concave faces 10A of the first substrate 10~~, the incident light is reflected and scattered efficiently, and ~~the~~ a display having a bright reflection display and wide angle of visibility are realized. These advantages of the present invention are due to the control of the depth and pitch of the concave faces 12A shown in FIG. 2 in the range as described hereinabove and due to the spherical surface of the inner face of the concave faces 12A.

In detail, the depth and pitch of the concave faces 12A are formed under control, the inclination of the inner surface of the concave faces 12A that controls the light reflection angle is controlled in a certain range. As the result, the reflection efficiency of the metal reflection film 12 can be controlled within a certain range.

Furthermore, because the inner surface of the concave faces 12A is symmetrically spherical in all the directions, the above-mentioned reflection efficiency can be obtained for all the directions of the metal reflection film 12. To sum up, the bright display can be seen from all the directions.

The convex/concave ~~faces 10A~~ face 10A of the first substrate 10 is formed by hot-pressing a resin material sheet to shape it in the form of the first substrate 10 by use of a transfer die. The above-mentioned transfer die is made by ~~means of a method in which a diamond indenter is pressed on the surface of flat base material for transfer die such as stainless steel, and the configuration of the convex/concave faces 10A~~ face 10A shown in FIG. 2 is formed by use of an inversely convex/concave die.

The process conditions applied in the hot-pressing process such as temperature, pressure, and time may be selected suitably depending on the type of material and the size of the substrate 10. For example, the process temperature is preferably a temperature 10° C to 20° C lower than the heat-resisting temperature of the material of the first substrate 10. More in detail, in the case that, for

example, polyallylate resin sheet having a thickness of 0.3 mm is used for the substrate 10, the process condition for forming the convex/concave ~~faces 10A~~face 10A includes a process temperature of 170 ° C to 180 ° C, pressure of 100 to 200 kg/cm², and ~~the process time of 1 to 3 minutes.~~ Note however that, but these process conditions are merely one example, the process conditions is-are by no means limited to the above-mentioned conditions.

The convex/concave ~~faces 10A~~face 10A formed by hot-pressing is preferably formed on the ~~area~~entire face of the substrate 10 excepting the periphery of the substrate 10. The structure as described hereinabove has flat surface on the periphery of the substrate 10, and the overcoat film 14 can be fit on the substrate 10 firmly. As the result, the overcoat film 14 will not be separated from the substrate 10, and it is possible that the liquid crystal display apparatus 1 of the present invention retains high reliability for a ~~long~~number of years in ~~the a~~ high temperature and high humidity environment (for example, a temperature equal to or higher than 60 ° C and a humidity equal to or higher than 90 %).

Furthermore, because a hot-pressing method is used as a method for forming the convex/concave ~~faces 10A~~face 10A, a large ~~size~~substrate is may be hot-pressed, ~~and the~~This large hot-pressed substrate ~~is~~may then be divided into substrates 10 having a desired size. Therefore, a plurality of substrates 10 on which the convex/concave ~~faces~~

10Aface 10A are formed can be obtained in one operation efficiently.

As described hereinbefore in detail, according to the liquid crystal display apparatus of the present invention, the convex/concave configuration (~~the a configuration having the~~ in which continuous concave faces each have an inner surface that is a part of the spherical surface of continuous many concaves) is formed directly on the surface of the liquid crystal layer side of the substrate of the liquid crystal display apparatus having ~~the a~~ flexible substrate. As the result, the configuration of the liquid crystal display apparatus is made simpler than that of the conventional liquid crystal display apparatus and the manufacturing cost is reduced.

Next, ~~in the case that a reflection type liquid crystal display apparatus provided with a metal reflection film formed on the surface of the above-mentioned substrate where the convex/concave~~ face is formed is fabricated, the has an improved light reflectance is improved due to the above-mentioned surface configuration. As the result, a reflection type liquid crystal display apparatus having ~~the a~~ bright and easily viewable display and wide angle of visibility is realized.

In the case that a semi-transmission/reflection type liquid crystal display apparatus provided with a backlight for transmission display on the outside of the substrate having a metal reflection film with a film thickness of 80

Å to 300 Å is fabricated, ~~the~~ a bright reflection display is obtained due to the surface configuration of the above-mentioned substrate in the reflection mode in which the solar light or illumination is used as the light source for displaying an image. On the other hand, in the case of the transmission mode in which the light from a backlight is used as the light source for displaying an image, ~~the~~ a bright display is obtained due to the high transmittance of the metal reflection film. As the result, in both operation modes, a semi-transmission/reflection type liquid crystal display apparatus that displays a bright and easily viewable image is provided.

Furthermore, in the case that the film thickness of the metal reflection film of the above-mentioned semi-transmission/reflection type liquid crystal display apparatus is in the range from 80 Å to 100 Å, a semi-transmission/reflection type liquid crystal display apparatus that gives very bright display in the transmission mode is provided.

Particularly, because the inner surface of the concave faces formed on the above-mentioned substrate surface is a part of spherical surface, the light supplied from a backlight is enhanced by the lens effect, and the semi-transmission/reflection type liquid crystal display apparatus ~~gives~~ provides a bright transmission display ~~the~~ more. Furthermore, it is possible to employ a backlight of a lower light intensity because of the above reason, a

low power consumption liquid crystal display apparatus is realized.

Next, according to the liquid crystal display apparatus of the present invention, because a color filter is formed immediately on the metal reflection film, the parallax and the color deviation are reduced and the high quality display is realized.

Next, according to the liquid crystal display apparatus of the present invention, in the case that a colored substrate having the surface on which the convex/concave configuration is formed is used, the color of the substrate is used as the display color, and it is possible to give ~~the a display of higher color purity higher than that of the a display~~ obtained by means of orientation control of the liquid crystal molecule.

Next, according to the liquid crystal display apparatus of the present invention, in the case that the above-mentioned substrate is formed of resin such as polyallylate base resin, polycarbonate base resin, polyethersulphone base resin, or polyethylene terephthalate base resin, the substrate is rendered highly light transmissive and highly heat resistive. As the result, the layers can be formed on the substrate at a high temperature. A high quality liquid crystal display apparatus is provided thereby.

According to the present invention, in both cases that a semi-transmission/reflection type or a reflection

type liquid crystal apparatus is fabricated, a liquid crystal display apparatus that gives a bright display and wide angle of visibility is provided.

Furthermore, according to the present invention, the configuration is simplified to bring about reduced manufacturing cost of the liquid crystal display apparatus.

What Is Claimed Is:

1. A liquid crystal display apparatus comprising a pair of substrates disposed ~~so as to~~ face each other with interposition of a liquid crystal layer, at least one of the substrates ~~is being~~ a flexible substrate, wherein ~~many~~ a plurality of concave faces having the a spherical inner surface that is a part of the spherical surface are formed continuously on the a surface of at least one of the substrates, ~~the substrate surface out of the pair of substrates that is facing to the liquid crystal layer side.~~

2. The liquid crystal display apparatus according to claim 1, wherein ~~the a~~ depth of a the concave faces ranges from 0.1 μm to 3 μm , ~~the an~~ inclination distribution of the inner surface of a the concave faces ranges from -30 degrees to +30 degrees, and ~~the a~~ pitch between adjacent concave faces ranges from 5 μm to 50 μm .

3. The liquid crystal display apparatus according to claim 1, wherein a metal reflection film is formed on the substrate surface ~~on which many concaves having the inner surface that is a part of the spherical surface are formed continuously.~~

4. The liquid crystal display apparatus according to claim 3, wherein ~~the a~~ film thickness of the metal reflection film ranges from 80 Å to 300 Å.

5. The liquid crystal display apparatus according to claim 3, wherein ~~the a~~ film thickness of the metal reflection film ranges from 80 Å to 100 Å.

6. The liquid crystal display apparatus according to claim 3, wherein a color filter is formed directly on the metal reflection film.

7. The liquid crystal display apparatus according to claim 1, wherein the substrate surface ~~on which many concaves having the inner surface that is a part of the spherical surface are formed continuously~~ is colored.

8. The liquid crystal display apparatus according to claim 1, wherein the flexible substrate ~~consists of~~ comprises one of a polyallylate base, polycarbonate base, polyethersulphone base, ~~or and~~ polyethylene terephthalate base resin.

09975344-101001

ABSTRACT OF THE DISCLOSURE

The invention provides a liquid crystal display apparatus having a flexible substrate that realizes the bright and high quality display. A liquid crystal display apparatus ~~1~~ in which ~~has~~ a liquid crystal layer ~~30~~ is interposed between a pair of flexible substrates ~~10~~ and ~~20~~ that ~~are faced~~ face each other, and ~~many~~ a plurality of concave faces having ~~the~~ a spherical inner surface ~~that is a part of the spherical surface~~ are formed continuously on the surface of the substrate ~~10~~ that ~~is facing to~~ faces the liquid crystal layer ~~30~~ side ~~is employed~~.